

DARATARD[®] P88

Water-reducing initial set retarder

Product Description

DARATARD[®]P88 admixture is an aqueous dark brown solution of selected hydroxylated organic compounds. It is ready-to-use since the ingredients are factory pre-mixed in exact proportions to minimise handling, eliminate mistakes and guesswork. Daratard P88 complies with the chemical admixture specifications for concrete: SS 320:1987.

One litre weighs approximately 1.13kg ± 0.02kg.

Application

Daratard P88 provides better slump retention than normal retarding admixtures, and retards the initial and final set of concrete throughout the recommended dosage range. In the recommended dosage range, Daratard P88 also gives water reduction of typically 8% to 12%.

Daratard P88 admixture is recommended for use in all concrete where superior workability, extended setting times and pumpability quality are desired in applications, e.g., hot weather concreting application, large volume concrete pours.

Product Advantages

- Improved working time for placing concrete with better slump retention.
- Extended setting time to facilitate sufficient delivery, placement, vibration or compaction time.
- Increased compressive, flexural and bonding strength with less concrete mix water.
- Better pumpability, finishability and concrete appearance with improved plasticity and workability.
- Reduced tendency to bleeding and segregation.
- Better cost economics in concrete production for a given strength and slump.
- Reduced water permeability to make concrete more watertight, thus improving concrete durability.

Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.

Packaging

Daratard P88 is available in bulk and 205L drums. Daratard P88 may freeze at a temperature below -2°C. If frozen, thaw it till it is completely dissolved with mechanical agitation before use. Daratard P88 contains no flammable ingredients.



Addition Rates

Daratard P88 dosage ranges are recommended to be between 300 and 600mL /100kg of cementitious materials. The actual amount of Daratard P88 to be used will depend on the extension of setting time required under the different job conditions. Longer setting times or higher temperatures will typically require higher addition rates. Conversely, the addition rates will be lesser for shorter extensions of time. Consult your local GCP representative for assistance in determining the dosage rate for optimum performance.

Compatibility with Other Admixtures

Daratard P88 admixture is compatible in concrete with all other admixtures from GCP Applied Technologies. Daratard P88 admixture can be used alone as a single admixture or in combination with other admixtures to achieve cost-effective customised performance. If used in combination with other admixtures, each admixture should be added separately

Health and Safety

Please refer to the Daratard P88 Material Safety Data Sheet or consult GCP Applied Technologies.

gcpat.sg | For technical information: asia.enq@gcpat.com

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Daratard is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2017 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP (Singapore) Pte. Ltd, 25 Tanjong Penjuru, Singapore 609024.

This document is only current as of the last updated date stated below and is valid only for use in Singapore. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.sg. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-15

gcpat.sg/solutions/products/daratard-p88