

DCI® S

For corrosion protection of steel-reinforced concrete

Product Description

DCI® S Corrosion Inhibitor chemically inhibits the corrosive action of chlorides on reinforcing steel and prestressed strands in concrete. It has been formulated to provide set time characteristics similar to untreated concrete at 22 °C. DCI S is a liquid added to concrete during the batching process. One litre of DCI S weighs approximately 1.28kg ± 0.02kg and contains a minimum of 30% calcium nitrite. DCI S complies to AS 1478.1 as a Type AC.

Applications

DCI S is recommended for all steel-reinforced, post-tensioned and prestressed concrete that will come in contact with chlorides from deicing salts or a marine environment. Examples are chloride contaminated soil, support structures, bridge decks, prestressed members, and structures in marine environments. It may also be used in concrete where chlorides are added during manufacture.

Facts about Steel Corrosion

Corrosion occurs in the presence of oxygen, moisture, and an electrolyte. As chlorides attack the reinforcing steel, the salt intensifies the electrolyte properties of concrete, thereby creating a corrosion cell. As the corrosion reaction occurs, rust is formed. It migrates away from the reinforcing bar, leaving more iron to be corroded. This process continues and two situations develop:

- The reinforcing bars disintegrate, which reduces the flexural strength of the concrete structure; and,
- Iron, as it oxidizes, expands to four times its original volume. This expansion results in physical disruption of the concrete. Typical results are cracks, stains, crazing, spalling and pot holes; all of which are safety hazards.

Chemical Inhibition of Corrosion

DCI S Corrosion Inhibitor is a system containing calcium nitrite which interacts with the embedded steel in concrete to prevent salt attack. By chemically reacting with the reinforcing, a barrier is formed which prevents chloride penetration. Corrosion initiation is delayed and corrosion rates are kept under control. Once corrosion has been inhibited, physical disruption of the concrete due to rust formation will not occur.

When added to concrete in sufficient quantity as determined by the anticipated chloride ion content of the concrete over the design life of the structure, DCI S maintains an active corrosion-controlling system within the concrete matrix.

Addition Rates

Recommended addition rates range from 5 to 30L / m³. The level of corrosion protection increases in proportion to the dosage. The



project specification will indicate the addition rate. In the absence of a specified dosage, or where needed to offset premixed chlorides, call your local GCP representative.

Cement Compatibility

DCI S Corrosion Inhibitor is compatible with all types of portland cement, and concretes containing pozzolans. However, due to the significant variation between cements, there may be differences in response to DCI S. This is especially true with respect to the effect on setting time, which also influences slump retention.

Mix Water Reduction

Mix water adjustment is essential to account for the water in DCI S and thus maintain the desired water-cement ratio. The mix water added at the batch plant must therefore be reduced to compensate for the addition of the corrosion inhibitor. One litre of DCI S contains 0.84kg (0.84L) of water. A high-range water reducer such as ADVA® may be used to maintain workability in low water-cement ratio concrete.

Compatibility with Other Admixtures

DCI S Corrosion Inhibitor can be used in concrete with other admixtures, including air-entraining admixtures, water reducers, superplasticisers, set-retarders, pozzolans and microsilica, without impeding their performance. Each admixture must be added separately. Individually added, each will deliver exactly the results desired.

Concrete Set Time

DCI S is a neutral-set corrosion inhibitor formulated not to affect concrete setting times at or below 22 °C, which may also aggravate slump loss. In some cases, environmental conditions may require the addition of an accelerator or a retarder. In these cases, DaraSet®, a non-chloride accelerator, or a retarder such as Daratard® 17, both from GCP Applied Technologies, may be added separately to the concrete mix.

Air Entrainment

DCI S Corrosion Inhibitor at the normal addition rates may moderately reduce the entrained air content. It may be necessary to increase the dosage of the air-entraining admixture to compensate. Project specifications for DCI S generally will show requirements of $6\frac{1}{2} \pm 1\frac{1}{2}\%$ in the plastic or fresh concrete.

Preconstruction Trial Mix

It is strongly recommended that trial mixes be made several weeks before construction start up. This will allow the concrete producer an opportunity to determine the proper batching sequence and amounts of other admixtures needed in order to deliver the required concrete mix to the job-site. Due to the cement response variation it is vital that set time and slump retention of the proposed mix be thoroughly tested and evaluated in the light of job requirements. GCP's broad experience with this product can help the concrete producer deliver satisfactory product regardless of the mixture proportions. Contact your local GCP representative for help with trial mixes.

Finishing and Curing

Concrete containing DCI S Corrosion Inhibitor finishes with standard tools and techniques. It is no different from any other air-entrained, low water-cement ratio mix in terms of finishability. Curing procedures must follow ACI 302 and ACI 308.

Packaging and Availability

DCI S Corrosion Inhibitor is available in bulk quantities by GCP Applied Technologies metered systems, or in 208L drums.

Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.

Freezing Point

DCI S freezes at approximately -15 °C, but its corrosion inhibition and strength gain properties are completely restored by thawing and thorough agitation.

Health and Safety

See DCI S Material Safety Data Sheet or consult GCP Applied Technologies.

gcpat.com | For technical information: asia.enq@gcpat.com

Australia 1800 855 525 New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898
India: Chennai +91 44 6624 2308 Delhi +91 124 402 8923 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800
Malaysia +60 3 9074 6133 Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

DCI, DataSet and Daratard are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

Printed in Singapore | 02/16 | 200-DCI-160



gcp applied technologies

GRACE CONSTRUCTION & PACKAGING