



Gelacryl™

Gelacryl is a two-component, acrylic-based injection resin developed for waterproofing, control of water infiltration and stabilising and coagulating a variety of loose soils

Product Description

Gelacryl™ is an acrylic-based, hydrophilic gel, consisting of two-components: a resin and an initiator which are pumped with a twin piston pump at a 1/1 ratio. Once polymerised, Gelacryl forms a resilient, elastomeric gel.

- Resin : Gelacryl
- Catalyst : TE 300
- Initiator : SP 200
- Decelerator : KF 500

Product Advantages

- Gelacryl is injected with a twin piston, 1/1 ratio pump
- Gelacryl is delivered on site with a composition of 45% solids which can be diluted to 22% solids, depending on the nature of the application. In diluting the basic material, the viscosity can be adapted depending on the site requirements
- The low viscosity of Gelacryl ensures a deep penetration in the joint and the soil around the joint
- Exhibits very low permeability for long lasting waterproofing
- Non-flammable
- No environmental labelling required
- Poly-acrylate resin, free of acrylamides
- Has a very good overall chemical resistance and is resistant to petroleum, mineral/vegetable oils and greases (*)

(*) For chemical resistances please contact your GCP representative.

- Sealing of cracks in concrete and rock formations.
- Sealing of tunnel liners.
- Mixed with cement for the waterproofing and consolidation of structures and voids.

Application

Consult the Material Safety Data Sheet (MSDS) before mixing and/or handling.

1. Composition

- The injection grout needs to be prepared immediately before the injection. Do not dilute the resin to less than 23% solids when injecting.

Component 1	Component 2
Gelacryl	Water
TE 300	SP 200

- After preparation, the components are injected simultaneously at a ratio of 1/1.

2. Preparation

Component 1

- Gelacryl vessel. Add the required quantity of TE 300 catalyst to the Gelacryl resin. Gelacryl and TE 300 need to be thoroughly mixed.

Component 2

- SP 200 vessel. The vessel is first filled with the required quantity of water as the Gelacryl vessel after which the SP 200 is added. The mixture is thoroughly mixed.

Field of Application

- Water control during tunnelling operations.
- Curtain grouting.
- Waterproofing of underground structures in concrete or masonry (cellars, underground car parks).

3. Gel times (typical mixtures)

- Depending on the concentrations of TE 300 catalyst and SP 200 initiator in their respective blends, varying gel times can be obtained. Air, material and background temperatures will

also influence gel times. The pH and the nature of the injection substrate will also affect gel times. The following typical gel times can be obtained by mixing the components according to the following formulations.

T (°C)	Product	Resin (l)	TE300 (l)	Water (l)	SP200 (kg)	Number of containers	Geltime
5	GA	42.00	1.70	42.00	1.80	4	1'
5	GA	42.00	1.70	42.00	1.35	3	2'
5	GA	42.00	1.70	42.00	0.90	2	3'
10	GA	42.00	1.30	42.00	1.80	4	1'
10	GA	42.00	1.30	42.00	0.90	2	2'
10	GA	42.00	1.30	42.00	0.45	1	3'
15	GA	42.00	1.00	42.00	1.35	3	1'
15	GA	42.00	1.00	42.00	0.90	2	2'
15	GA	42.00	1.00	42.00	0.45	1	3'
20	GA	42.00	0.80	42.00	1.35	3	1'
20	GA	42.00	0.80	42.00	0.90	2	2'
20	GA	42.00	0.80	42.00	0.45	1	3'

4. Injection

- The injection work should be carried out with a twin piston, 1/1 ratio pump (IP 2C-Gel). Please read the relevant Technical Data Sheet. For injection procedure, please read the Injection Manual.
- Delayed gel times (for example for soil injections) can be reached by adding KF 500 decelerator. Contact our technical department for correct formulations.

Appearance

Gelacryl Resin: Green liquid

TE 300: Transparent liquid

SP 200: White salt

KF 500: Orange liquid

After curing, product turns into a flexible gel, which remains flexible under water.

Consumption

Has to be estimated by the engineer or operator and depends on width and depth of the cracks and voids to be filled.

Packaging

Gelacryl

25 kg plastic jerry-can

1 pallet = 24 jerry-cans

TE 300

25 kg plastic jerry-can

1 pallet = 24 jerry-cans

SP 200

0.45 kg plastic bottle

1 box = 22 bottles

1 pallet = 24 boxes

KF 500

25 kg plastic jerry can

1 pallet = 24 jerry-cans

Storage

Gelacryl, TE 300, SP 200 and KF 500 should be stored in a frost-free environment under cover, clear of the ground, in the original closed packaging.

Storage temperature must be below 35°C.

Shelf life: 1 year.

Accessories

To be ordered separately

- IP 2C-Gel air driven twin piston pump.

- Packers and connectors.

(Please consult the relevant Data Sheet).

Health and Safety

Gelacryl is classified as irritating.

Always wear appropriate protective gear: rubber gloves, goggles and boots. In case of contact with the eyes, flush with water for 15 minutes. If swallowed, call a physician immediately.

For full information, consult the relevant MSDS.

Technical Data/Properties

Property	Value	Norm
Gelacryl		
Density	Approx. 1.17kg / dm ³	ASTM D-1638
Viscosity	Approx. 18 mPas at 25 °C	ASTM D-1638
Solids	Approx. 45%	ASTM D-1010
Boiling point	100 °C	Test DNC
Freezing point	< -20 °C	Test DNC
Solubility in water	100%	Test DNC
Catalyst TE 300		
Concentration	Approx. 85%	Test DNC
Initiator SP 200		
Density	Approx. 1.9kg / dm ³	ASTM D-1638
Solubility in water	Approx. 79%	Test DNC
Decelerator KF 500		
Concentration	10%	Test DNC
Dilution	Clean tap water	
Cured resin based on a 22% solids mixture.		
Solubility	Insoluble in water and petroleum derivatives	Test DNC
Expansion in contact with water	< 30%	Test DNC

gcpat.com | For technical information: asia.enq@gcpat.com

Australia 1800 855 525 email: au.sbmsales@gcpat.com New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888
 Hong Kong +852 2675 7898 India +91 124 488 5900 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800
 Malaysia +60 3 9074 6133 Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Gelacryl is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

Printed in Singapore | 11/16 | 500-Gelacryl-17



gcp applied technologies