

DARACEM[®] S21M

Superplasticiser for the production of high workability concrete

Product Description

DARACEM[®]S21M is a ready-to-use aqueous solution of a modified naphthalene sulfonate. Daracem S21M is a high range water reducer, commonly referred to as a superplasticiser. It is a low viscosity liquid, which has been formulated by the manufacturer for use as received. Daracem S21M contains no added chloride. Daracem S21M is formulated to comply with the chemical admixtures specifications for concrete: ASTM C494 Type F. One litre of Daracem S21M weighs approximately 1.17kg \pm 0.02kg.

Dispersion

Daracem S21M is a superior dispersing admixture having a marked capacity to disperse the cement agglomerates normally found in a cement-water suspension. The capability of Daracem S21M, in this respect, exceeds that of normal water-reducing admixtures.

Product Advantages

- Daracem S21M, in prestress/precast work, can be used to substantially reduce or eliminate the high energy requirements of external heat for accelerated curing.
- It is excellent for early strength development of slag cement concrete.
- It is compatible with a wide range of cements.
- It can produce high slump flowable concrete at no loss in strengths.
- It produces low water-cement ratio concrete and therefore, high strengths.
- It aids in rapid discharge of concrete from truck mixers thereby reducing on-the-job time and improving mixer utilisation.

Application

Daracem S21M produces concrete with extremely workable characteristics referred to as high slump, flowing concrete. Daracem S21M also allows concrete to be produced with very low watercement ratios at low or normal slumps.

Daracem S21M is ideal for use in prestress, precast, bridge deck or any concrete where it is desired to keep the water-cement ratio to a minimum and still achieve the degree of workability necessary to provide easy placement and consolidation.

Daracem S21M will also fluidise concrete, making it ideal for tremie concreting or other applications where high slumps are desired.

Compatibility with Other Admixtures

Most water reducers or water-reducing retarders are compatible with Daracem S21M as long as they are separately added to the concrete. Pretesting of the concrete should be performed to optimise dosages and addition times of these admixtures. The admixtures should not be in contact with each other before they enter the concrete. Daracem S21M is recommended to be used in ambient temperatures above 15 °C. Daracem S21M should not be used in concrete subject to more than 70 °C heat curing. Daracem S21M is not to be used with polycarboxylate-based admixtures such as ADVA®.



Addition Rates

Addition rates of Daracem S21M can vary with type of application, but will normally range from 400 to 1,500mL / 100kg of cementitious material. In most instances the addition of 700 to 1,000mL / 100kg of cementitious material will be sufficient. When combined with Grace DARATARD® or WRDA®, Daracem S21M dosage rates can be effective from 100 to 400mL / 100kg of cementitious material, when added separately to the mix. At a given water-cement ratio, the slump required for placement can be controlled by varying the addition rate. Should job site conditions required using more than the recommended addition rates, please consult your local GCP representative.

Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.

Packaging

Daracem S21M is available in bulk and in 205L drums. Daracem S21M contains no flammable ingredients. It will begin to freeze at approximately 0 °C, but will return to full strength after thawing and agitation. In storage and for proper dispensing, Daracem S21M should be maintained at temperatures above 0 °C.

Health and Safety

See Daracem S21M Material Safety Data Sheet or consult GCP Applied Technologies.

gcpat.sg | For technical information: asia.enq@gcpat.com

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Daracem, WRDA, Daratard and ADVA are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2017 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP (Singapore) Pte. Ltd, 25 Tanjong Penjuru, Singapore 609024.

This document is only current as of the last updated date stated below and is valid only for use in Singapore. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.sg. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-15

gcpat.sg/solutions/products/daracem-s21m